

	Moisture %MAX.	App.Density g/cc	Hardness MIN.	Ash %MAX.	Iodine mg/g MIN.	Butane MIN.	Molasses MIN.	Methylene Blue MIN.	WSA** %MAX.	pH	Floaters % MAX.	Size*
<b>LIQUID PHASE APPLICATION</b>												
AG-900	2	0.46-0.54	90	11-20	900	NA	NA	160	0.5	NA	5	6X12, 8X30, 1240
AG-1000	2	0.46-0.54	90	11-20	1000	NA	NA	200	0.5	NA	5	6X12, 8X30, 1240
AG-900W	2	0.46-0.54	90	8	900	NA	NA	200	0.3	6.5-8.0	NA	6X12, 8X30, 1240
REG-900	2	0.35-0.50	95	12	900	NA	NA	180	NA	6.5-8.0	0	8x30, 12x40
REG-1000	2	0.35-0.50	95	12	1000	NA	NA	180	NA	6.5-8.0	0	8x30, 12x40
AG-1000W	2	0.46-0.53	90	8	1000	NA	NA	NA	0.3	6.5-8.0	NA	6X12, 8X30, 1240
AGU-900	2	0.45-0.54	90	10	900	NA	200	NA	0.5	NA	NA	6X12, 8X30, 1240
AGU-900W	2	0.45-0.54	90	8	950	Na	200	Na	0.2	6-8	NA	6X12, 8X30, 1240
AG-1000C	3	0.46-0.52	97	4	1000	NA	NA	NA	2	NA	NA	8X30,12X30, 1240
AG-1100C	3	0.46-0.52	97	4	1100	NA	NA	NA	2	NA	NA	8X30,12X30, 1240
AG-1100AWC	3	0.46-0.52	97	3	1100	NA	NA	NA	0.2	6.5-6.0	NA	8X30,12X30, 1240
AG-500P	4	0.44-0.52	NA	15	500	NA	NA	NA	NA	NA	NA	-200, -325
AG-800P	4	0.44-0.52	NA	15	800	NA	NA	NA	NA	NA	NA	-200, -325
CNS	3	0.43-0.52	95	NA	1050	23.5	NA	NA	NA	NA	NA	3mm, 4mm, 8X30
RAG-900D	3	0.25-0.40	90	***	900	NA	250	NA	NA	6.5-8.0	NA	6X10, 6X20, 8x30
<b>VAPOR PHASE APPLICATION</b>												
VG-60	2	0.47-0.53	95	12	NA	23.5	NA	NA	NA	NA	NA	1 - 9 mm
VG-70	2	0.47-0.53	95	12	NA	27.5	NA	NA	NA	NA	NA	2 - 9 mm
VG-60S	2	0.38-0.45	93	14	NA	23.5	NA	Na	NA	NA	NA	4X6
VG-70C	2	0.45-0.52	95	6	1050	25.5	NA	NA	NA	NA	NA	4X6, 6X8, 830, 1240
VG48C	2	0.45-0.52	97	6	NA	23.5	NA	NA	NA	NA	NA	4X8
LC-325	5	0.44-0.52	NA	****	500	NA	250	NA	NA	NA	NA	-325
VGR-50	3	0.47-0.58	95	10	NA	21.5-27.5	NA	NA	NA	NA	NA	2 - 5mm
VGX-60	3	0.47-0.58	95	10	1000	23.5	NA	NA	NA	NA	NA	1 - 4mm
VGH-80	3	0.41-0.49	90	14	NA	23.5-29.5	NA	NA	NA	NA	NA	2 - 5mm

\* Size: The standard size is listed in table. It could be varied based on the request.

\*\* WSA: Water Soluble Ash.

\*\*\* ORTHOPHOSPHATE is ZERO.

\*\*\*\*Decolorization is 60%min.